

RAMCO

RAMCOTE 1200 PKI QUIK COTE

RAMCOTE 1200 and QUIK COTE are “one coat” insulating and finishing products composed of mineral fiber, binders and corrosion inhibiting agents. It dries to a white monolithic finish over applied surfaces. It is blended to produce excellent adhesion and a smooth finish.

These cements can be poured, palmed, troweled or air-gunned into place and should always be applied to the full thickness specified in one application. They have exceptionally good adhesive qualities and may be applied directly to the metal surfaces or over insulated and refractory surfaces.

PHYSICAL AND MECHANICAL CHARACTERISTICS

SPECIFICATIONS		“K” FACTOR	
ASTM	C-449	MEAN TEMP.	“K”
		200°F	0.85
		400°F	0.96 1.05
		600°F	
	Service Temperature	1200°F	
	*Coverage per 100 lbs.	30 bd. ft. (wet or dry)	
	*Water/Cement Ratio (By Weight)	1.1 - 1.25 (6½ - 7½ gal.)	
	Shrinkage	Negligible	
	*Density (Installed)	30-34 lbs./cu. ft.	
	Initial Setting	2½ to 3½ hours	

Corrosion
(Steel)

None

(Aluminum)

Aluminum must be painted

Moisture and Water Resistance

Does not soften after firmly set

Fire Resistance

Non-combustible

Fire Hazard Classification Rating does not exceed:

Flame Spread	25
Fuel Contributed	50
Smoke Developed	50

Surface Treatment - Water Base Paints

Any time after setting

-Oil Base Paints

Only after thoroughly dry

-Emulsion Weatherproofing

Any time after setting

-Asphalt Base Cut-Backs

Only after

thoroughly dry Packaging 4

5 lb. Multiwall

Bags

Polyethylene liner

DOES NOT CONTAIN ASBESTOS FIBERS

WARNING: DUST PARTICLES OF THIS CEMENT IN DRY FORM MAY BE HARMFUL TO YOUR HEALTH - WE RECOMMEND THE USE OF DUST RESPIRATORS.

For more information about **RAMCO or PKI**
products, contact

RAMCO INSULATION, INC.

Office: 417-781-8855 FAX: 417-781-9192

P.O. Box 2173, Joplin, MO 64803

www.ramcoinsulation.com